

**CONTRACT CRYSTAL GROWTH  
AND  
FABRICATION SERVICES**

**DTIC**  
**ELECTE**  
**MAY 08 1990**  
**S D** <sup>CB</sup>

Quarterly Technical Report # 4

**AD-A221 357**

Period: February 1990 through April 1990

Report Date: May 1, 1990

Contract Number: N00014-89-C-2222

Contributors: J. E. Creamer, R. C. Acklin, M. H. Randles

Prepared by: M. H. Randles  
Airtron Division of Litton Systems, Inc.  
PO Box 410168  
Charlotte, N. C. 28241-0168

**DISTRIBUTION STATEMENT A**

Approved for public release;  
Distribution Unlimited

Submitted to: Dr. Charles Marquardt, COTR  
Naval Research Laboratory  
Code 6551  
4555 Overlook Ave., SW  
Washington, D. C. 20375-5000

## SUMMARY

✓ This program is intended to give the scientists at the Naval Research Laboratory the ability to evaluate new solid state laser crystals. During the fourth quarter of this contract only one growth run was performed and three parts were fabricated from this crystal.

## CRYSTAL GROWTH

✓ The crystal requested and grown was Cr,Tm:YALO. The melt composition is listed in Table 1. It was assumed that the distribution coefficients are unity and that the crystal composition will be the same as the melt.

TABLE 1: Composition

| <u>Growth Run</u> | <u>Melt composition</u>   | <u>Nominal Doping</u><br>at% (cm <sup>-3</sup> )                     |
|-------------------|---|--|
| NRL-9             | Y <sub>0.958</sub> Tm <sub>0.042</sub> Al <sub>0.996</sub> Cr <sub>0.004</sub> O <sub>3</sub> | 4.2 % Tm (8.2x10 <sup>20</sup> )<br>0.4 % Cr (7.8x10 <sup>19</sup> ) |

The growth conditions are listed in Table 2. ✓ The crystal was grown with a b-axis YALO seed. At about the time full diameter was reached the crystal developed twins apparently from several pieces of iridium that attached to the surface at that point. The oxygen level can be adjusted on future runs to decrease the occurrence of iridium metal. As a result of the twinning some of the crystal was badly cracked, but a 63.5mm laser rod was extracted. This rod does contain some twin planes however. A 5mm spectroscopic cube was also fabricated from the twinned region. Another small rod of 5mm diameter by 20mm long was cut from the boule cone and is twin free. → JET/G

TABLE 2: Growth Conditions

| <u>Growth Run</u> | <u>Pull Rate</u><br>mm/Hr | <u>Rotation</u><br>RPM | <u>Oxygen</u><br>% | <u>Average</u><br><u>Diameter</u><br>mm | <u>Length</u><br><u>at Diam</u><br>mm | <u>Fraction</u><br><u>Crystallized</u><br>% |
|-------------------|---------------------------|------------------------|--------------------|---|---------------------------------------|---|
| NRL-9             | 1.5                       | 15                     | 0.25               | 21x25                                   | 125                                   | 34  |

## FABRICATION

Rods of 5x63.5 and 5x20mm were cut and polished. The long rod has laser quality end finishes and the other is for spectroscopic evaluation. A spectroscopic cube 5x5x5 mm was also fabricated. The residual boule sections were delivered also.

## PLANS FOR NEXT QUARTER

At this time no further runs have been scheduled.



STATEMENT "A" per Dr. C. Marquardt  
NRL/Code 6551  
TELECON

5/7/90

VG

|                    |                                     |
|--------------------|-------------------------------------|
| Accession For      |                                     |
| NTIS CRA&I         | <input checked="" type="checkbox"/> |
| DTIC TAB           | <input type="checkbox"/>            |
| Unannounced        | <input type="checkbox"/>            |
| Justification      |                                     |
| By <i>per call</i> |                                     |
| Distribution       |                                     |
| Availability Codes |                                     |
| Dist               | Avail and/or Special                |
| A-1                |                                     |